

# The O-Ring Store LLC



We make getting o-rings easy!

## **BUNA-N FDA 70 DUROMETER DATA SHEET FOR COMPOUND FDAB70**

### **Compound Features:**

- FDA compliance\* for use in food applications.
- Excellent resistance to petroleum products.
- Excellent water resistance.
- Resistance to ethylene glycol fluids.
- Works well with silicone grease or oil lubricants.
- Good low temperature flexibility.
- Good abrasion and wear resistance.
- Good compression set.
- Good Permeation resilience.

### **Compound Limitations:**

- Poor resistance to UV/sunlight, ozone, and weathering.
- Halogenated hydrocarbons.
- Poor resistance to ketones (MEK) and other strong solvents.
- Poor resistance to strong acids.
- Poor resistance to automotive and aircraft brake fluids.

### **Temperature Range:**

-40°F to +250°F (-40°C to +121°C)

### **ASTM Callout:**

ASTM D2000-99 Grade M2BG714 B14 EA14 F17 Z1=TR10

### **\*FDA per CFR 177.2600**

# The O-Ring Store LLC



We make getting o-rings easy!

ORIGINAL PROPERTIES					
Properties	ASTM Designation	Test Method	Unit of Measure	ASTM D2000 Specification	S70 Compound Property
Durometer	-	-	Shore A	75 ± 5	72
Tensile Strength			PSI (MPa)	2031 (14) Min.	2420 (17)
Elongation Resistance			%	250 Min.	310
Specific Gravity			-	-	1.24

HEAT AGE					
Properties	ASTM Designation	Test Method	Unit of Measure	ASTM D2000 Specification	S70 Compound Property
Durometer Change	-	70 Hours @ 100°C	Shore A	±15	+3
Tensile Strength Change			%	±30	+7
Elongation Resistance Change			%	-50	-21

COMPRESSION SET					
Properties	ASTM Designation	Test Method	Unit of Measure	ASTM D2000 Specification	S70 Compound Property
Original Deflection	B14	22 Hours @ 100°C	%	25 Max	18

WATER RESISTANCE					
Properties	ASTM Designation	Test Method	Unit of Measure	ASTM D2000 Specification	S70 Compound Property
Durometer Change	EA14	70 Hours @ 100°C	Shore A	±10	+2
Volume Change			%	±15	+6.2

LOW TEMPERATURE RETRACTION					
Properties	ASTM Designation	Test Method	Unit of Measure	ASTM D2000 Specification	S70 Compound Property
Durometer Change	Z1	-	°C	-	-30.5

Information within is believed to be accurate and reliable. However, The O-Ring Store, LLC makes no warranty, expressed or implied, that parts supplied in this material will perform satisfactorily in specific applications. It's the customer's responsibility to evaluate the material prior to use.

1847 Wilma DR - Clarkston, WA 99403 | Phone (208) 413-6377 Fax (208) 413-6719